

RS MaxPox[®] two-component epoxy resin systems

MaxPox[®] 15M

Resin component for processing with hardeners 20, 40, 70 and 120

Solvent- and filler-free



MaxPox[®] 20

Hardener component for processing with MaxPox[®] 15M resin

Working time at 20 °C approx. 25 min.

Suitable for cold hardening, hot hardening with water or steam



MaxPox[®] 40

Hardener component for processing with the resin MaxPox[®] 15M

Working time at 20 °C approx. 40 min.

Suitable for cold hardening, hot hardening with water or steam



MaxPox[®] 70

Hardener component for processing with MaxPox[®] 15M resin

Working time at 20 °C approx. 70 min.

Suitable for cold hardening, hot hardening with water or steam





MaxPox[®] 120

Hardener component for processing with MaxPox[®] 15M resin

Processing time at 20 °C approx. 120 min

Hot hardening with water or steam

MaxPox[®] Fill

Filled and yellow colored two-component epoxy resin system

High viscosity for good grip in the carrier material

Application time at 20 °C approx. 30/60/90 min (depending on hardener components)

Hot and cold hardening possible

MaxPox[®] Thermo

Red colored two-component epoxy resin system

High temperature resistance up to 90 °C

Long processing time at 20 °C approx. 16 h

Not suitable for cold hardening, hot hardening with water or steam